Interdrain GM

Product specifications



Product description:

Geocomposite Intergrain GM is a geonet made form high-density polyethylene (HDPE) laminated by polypropylene (PP) geotextile on one side. The geonet is made from fibres which intersect at 60° and this pattern creates channels with high flow capacity under pressure and also at very low gradients.


Main uses: horizontal drainage of embankments and roads, railway and tram tracks and other trafficked areas. Vertical drainage of retaining structures, bridges, tunnels and other underground constructions, drainage of playgrounds, waste deposits, landfills etc.

- effective drainage geocomposite with long life span
- nigh drainage capacity even under pressure

Function:







Certificates:



	Tensile Strength		Elongation		Dynamic Perforation	Static	Thickness at			Roll			
					(Cone drop	Puncture	20	200					
Interdrain	longitudinal	transverse	longitudinal	transverse	test)	(CBR)	kPa	kPa	Weight	width	length	area	weight
	[kN/m]	[kN/m]	[%]	[%]	[mm]	[kN]	[mm]	[mm]	$[g/m^2]$	[m]	[m]	[m²]	[kg]
						EN ISO							
		EN ISO	10319		EN 918	12236	EN 964-1		EN 965			* * * * * * * * * * * * * * * * * * *	
GM 412	12	9	40	50	10	1,6	4,5	4,0	620	2	50	100	62
GM 512	13	10	40	50	10	1,7	5,5	5,0	770	2	50	100	77
GM 612	13	10	40	50	10	1,8	6,3	5,8	960	2	50	100	96

Suplier of product: **GEOMAT s.r.o.**

More information about this product on www.geomat.eu/en

Page 1 of 2 TS_GMX_EN_A_20_06

	Water permeability in						
Interdrain	20 kPa	50 kPa	200 kPa	Opening Size (for geotextile)			
	[l/m/s]	[l/m/s]	[l/m/s]	[mm]			
		EN ISO 12958	EN ISO 12956				
GM 412	1,26	1,11	0,76	0,1			
GM 512	1,64	1,43	1,10	0,1			
GM 612	1,91	1,70	1,30	0,1			

Remarks

The product has on each side of the geotextile overlaps the size of at least 10 cm. These simplify installation and prevent the penetration of the soil.

Unless indicated otherwise, values are determined according to the applicable European standards and are valid as of the date of this document. Products are subject to continuous development and improvement and these values may change over time.

In case of requirement the delivery of products with different dimensions or other technical data or in the case of interest of technical consultation please contact technical department by e-mail: $\underline{technika@geomat.eu}$.

Suplier of product: **GEOMAT s.r.o.**

More information about this product on www.geomat.eu/en

Page 2 of 2 TS_GMX_EN_A_20_06